

Cowin Color Co., Ltd.

240 Thakham Road, Samaedam,
Bangkhunthian, Bangkok 10150 Thailand
Tel: 0-2453-1788 Fax: 0-2453-1799



www.cowincolor.com
ISO 9001:2000 Certified

Product Information

P-520 Underglaze Medium

This product has been special developed suitable for mixing with underglaze color powder for banding and painting on bisques. A suitable mixing ratio will give a slow drying to allow extended working time, make it smooth appearance and colors are not overlapped or superimposed.

After drying about 3-4 hours, the colors will "**harden on**" and obtain good absorbtion of glazing. The media can be easily burnt out in the early stage of firing without residue, remaining only the designed colors.

Packaging : Plastic container 5 Kg, 25 Kg.

Typical Properties

| | |
|---------------------|---|
| Chemical Nature | A water solution of a modified polymer and polyethylene glycol containing wetting agent and a small quantity of a fungicide |
| Appearance | Hazy viscous liquid |
| Solubility | Water-soluble |
| Viscosity (Gardner) | 190 cps max.? |
| Thinner/Cleaner | Water |
| Mixing Ratio | Color/Medium/Water = 10 : 3-5 : 5 |

12-08-07